



## Technical Data Sheet

### CHEM LINK

#### Construction & Maintenance

Telephone: 800-826-1681

Fax: 269-679-4448

353 E. Lyons Street

Schoolcraft, MI 49087

[www.chemlink.com](http://www.chemlink.com)

Last Revision: 04/22/16

Document No. DS2370

### Description

For use on virtually all roofs, **WebSeal** is designed to hold coatings, whether water or solvent based. **WebSeal** makes the roof water-tight prior to application of coating, creating a superior, faster method of waterproofing over conventional 3 course applications, eliminating dependence on the roof coating as a water barrier. **WebSeal** remains flexible to temperatures as low as -70° F making it virtually impossible to thermally shock the seam causing a leak.

**WebSeal** bonds to a wide range of surfaces including difficult roof materials such as EPDM, TPO, aged PVC, SBS, APP modifieds, asphalt BURs, coal tar BURs, plus all metal roofs, tiles, shingle, aluminum, galvanized steel, gypsum board, wood, polyethylene, propylene, polystyrene, fiberglass, brick, concrete, masonry, OSB, etc.

### Basic Use

**WebSeal** tape is used to seal roof joints (seams) and tears, flashings, copings, skylights, gutters, etc. Perfect for repairing and restoring roofs on mobile homes and RVs. Extremely flexible, with no memory, so **WebSeal** conforms to virtually any shape without springing back. **WebSeal** seals to itself so it can be cut and folded around an object. A top coat of roof coating is necessary for UV protection.

### Composition

**WebSeal** utilizes an advanced MicroSealant Technology, a 100% solids formulation of synthetic resins, thermoplastics and non-curing rubber with a built-in primer. It is bonded to a woven polyester backing for maximum conformability. The adhesive coating is protected by a silicone release liner, to be removed prior to application.

### Surface Preparation

Surface must be clean and dry. Moisture, dust, dirt or other foreign matter should be removed. Remove oil and grease, etc. with isopropyl alcohol or a non-residue cleaner such as acetone or lacquer thinner. Remove salt and other contaminants.

### Application

Install **WebSeal** over the repair area, removing the release liner gradually to prevent contamination of the adhesive prior to application. Rub or roll with pressure using your hand or steel roller to activate bonding process. This material may be applied to clean dry surfaces from 150° F to -20° F ambient. Treat surface with EternaPrime for installations from 40° F to -20° F ambient. A topcoat of roofing coating is necessary for UV protection.

Technical Data	
Adhesion	19 lbs/in width
Application temperature	150° F to -20° F ambient
Available widths	Up to 48"
Elongation	>500%
Flexibility temperature range	-70° F - >200° F
Low temperature flexibility	1/2" radius at -30° F
Pliability	No cracks in membrane
Shelf life	Up to 5 years
Standard roll sizes	2", 4", 6", 8", 12", 24", 36" x 50'
Standard case quantity	100 sq. ft. per case
Total thickness	30 mils (1 mm)
Water vapor test (ASTME 96B)	.005 grms / 100" sq. / 24 hrs. / 100° F
Values are typical performance properties and characteristics based on laboratory testing. This is intended as a guide for comparison purposes and does not constitute a specification or specification range.	



**NOTES:**



**Contractor Hot Line**

**800-826-1681**

[www.chemlink.com](http://www.chemlink.com)



All properties described in this document are derived from testing conducted in laboratory conditions. Properties and performance will vary depending on environmental conditions and application technique. Test and evaluate to determine appropriate usage. Visit [www.chemlink.com](http://www.chemlink.com) for the Safety Data Sheet, Technical Data Guides and full warranty for this product.

**CAUTION:** All statements and technical information in this document are based on tests or data that **CHEM LINK** believes is reliable. However, **CHEM LINK** does not warrant or guarantee the accuracy or completeness of this information. The user has sole knowledge and control of factors that can affect the performance of **CHEM LINK's** products in the user's intended application. It is the user's responsibility to conduct tests to determine the compatibility of **CHEM LINK's** product with the design, structure, and materials of the user's end product and the suitability of **CHEM LINK's** product for the user's method of application and intended use. The user assumes all risk and liability arising out of such use.

**LIMITED WARRANTY:** **CHEM LINK** warrants this product's performance, provided it is properly stored and applied within 1 year. If this **CHEM LINK** material is proved to be defective, return remaining product and purchase receipt for refund or replacement of product exclusive of labor or cost of labor. This is the sole and exclusive remedy for defects or failure of this product. User must read and follow the direction of the current Technical Data Guide and SDS prior to product use. User determines suitability of product for intended use and assumes all risks. Manufacturer shall not be liable for damages (including consequential or incidental damages) in excess of the purchase price, except where such exclusion or limitation is prohibited by state law. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, STATUTORY, EXPRESS OR IMPLIED INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE; except for the above express warranty given by manufacturer, the product is sold with all faults. **CHEM LINK** SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. This warranty gives you specific legal rights, and you may also have other rights in the U.S. which vary from state to state. For warranty claim information, call 800-826-1681.